

TECHNICAL DATA SHEET

PETRAFAS-34 PLUS



Slabs of stone wool for internal and external building objects for thermal, acoustic and fire insulation

OFFICIAL DOCUMENTATION:

Declaration of Performance:
No. PTRL-DoP/MW/26/162



Łukasiewicz
WIT

1454-CPR-1029

APPLICATION:

- external and partition walls insulated by ETICS system
- external monolithic, prefabricated and brick walls
- fire insulation of attics (reaction to fire classification A1)

PETRALANA S.A.
Konstytucji 74 Street
41-905 Bytom
Poland
+48 32 770 05 00
office@petralana.eu

PRODUCT CODE

PETRAFAS-34 PLUS MW-EN13162-T5-DS(70,90)-CS(10)20-TR10-WS-WL(P)-MU1-AW0,90-AFr15

DECLARED THERMAL CONDUCTIVITY COEFFICIENT λ_D

$\leq 0,034[W/(mK)]$

DECLARED PARAMETERS

DECLARED PROPERTIES OF THE PRODUCT ACC. TO EN 13162:2012+A1:2015	SYMBOL	CLASS OR TOLERANCE	UNITS
Class for thickness tolerances	T	T5	-1 mm / +3 mm [mm]
			-1 % / +3 mm [%/mm]
Dimensional stability under 70 °C and 90% humidity	DS(70,90)	$\leq 1,0$	[%]
Compressive stress at 10% deformation	CS(10/Y)	20	[kPa]
Tensile strength perpendicular to faces	TR	$\geq 10,0$	[kPa]
Sound absorption	AW	0,90	[N]
Short time water absorption	WS	$\leq 1,0$	[kg/m ²]
Long time water absorption	WL(P)	$\leq 3,0$	[kg/m ²]
Water vapour transmission	MU	MU1	[-]
Air flow resistivity	AFr	15	[kPa s/m ²]
Reaction to fire	RtF	A1	Euroclass

DECLARED THERMAL RESISTANCE R_D

d [mm]	50	60	80	100	120	140	150	160	180	200	220	240	250	-	-	-	-
R_D [m ² K/W]	1,45	1,75	2,35	2,90	3,50	4,10	4,40	4,70	5,25	5,85	6,45	7,05	7,35	-	-	-	-

DIMENSIONS AND PACKING

FORMAT OF PLATES			PACKAGES			PALLETS		
Length	Width	Thickness	No. of plates in a package	Cover surface of a package	Volume of a package	No. of plates on a pallet	Cover surface of plates on a pallet	Volume of plates on a pallet
[mm]	[mm]	[mm]	[pcs.]	[m ²]	[m ³]	[pcs.]	[m ²]	[m ³]
1000	600	50	6	3,60	0,180	16	57,60	2,880
		60	5	3,00	0,180	16	48,00	2,880
		80	3	1,80	0,144	20	36,00	2,880
		100	3	1,80	0,180	16	28,80	2,880
		120	2	1,20	0,144	20	24,00	2,880
		140	2	1,20	0,168	16	19,20	2,688
		150	2	1,20	0,180	16	19,20	2,880
		160	2	1,20	0,192	12+16	33,60	5,376
		180	2	1,20	0,216	12	14,40	2,592
		200	2	1,20	0,240	12	14,40	2,880
		220	2	1,20	0,264	12+8	24,00	5,280
		240	1	0,60	0,144	20	12,00	2,880
		250	1	0,60	0,150	16+20	21,60	5,400
-	-	-	-	-	-	-	-	-