

## TECHNICAL DATA SHEET

# PETRAROOF-H



Stone wool panels for thermal,  
acoustic and fire insulation

### OFFICIAL DOCUMENTATION:

Declaration of Performances:  
No. PTRL-DoP/MW/15/12



1454-CPR-1021

### APPLICATION:

flat roof insulation with stone wool in single  
and double layers

unventilated flat roofs insulation with high  
strength

### FACTORY:

PETRALANA S.A.  
Konstytucji 74 Street  
41-905 Bytom  
Poland  
+48 32 770 05 00  
office@petralana.eu

## PRODUCT CODE

PETRAROOF-H MW-EN13162-T5-DS(70,90)-CS(10)60-PL(5)550-WS-WL(P)-MU1

## DECLARED THERMAL CONDUCTIVITY COEFFICIENT $\lambda_D$

$\leq 0,039$  [W/mK]

## DECLARED PARAMETERS

DECLARED PROPERTIES OF THE PRODUCT ACC. TO EN 13162:2012+A1:2015	SYMBOL	CLASS OR TOLERANCE	UNITS
Class for thickness tolerances	T	T5	-1 mm / +3 mm [mm]
			-1 % / +3 mm [%/mm]
Dimensional stability under 70 °C and 90% humidity	DS(70,90)	$\leq 1,0$	[%]
Compressive stress at 10% deformation	CS(10/Y)	CS(10)60	[kPa]
Tensile strength perpendicular to faces	TR	NPD	[kPa]
Point load at 5mm deformation	PL(5)	$\geq 550,0$	[N]
Short time water absorption	WS	$\leq 1,0$	[kg/m <sup>2</sup> ]
Long time water absorption	WL(P)	$\leq 3,0$	[kg/m <sup>2</sup> ]
Water vapour transmission	MU	MU1	[-]
Air flow resistivity	AFr	NPD	[kPa s/m <sup>2</sup> ]
Reaction to fire	RtF	A1	Euroclass

## DECLARED THERMAL RESISTANCE $R_D$

d [mm]	30	40	50	100	150	-	-	-	-	-	-	-	-	-	-	-
$R_D$ [m <sup>2</sup> K/W]	0,75	1,00	1,25	2,55	3,80	-	-	-	-	-	-	-	-	-	-	-

## DIMENSIONS AND PACKING

FORMAT OF PLATES			PALLETS		
Length	Width	Thickness	No. of plates on a pallet	Cover surface of plates on a pallet	Volume of plates on a pallet
[mm]	[mm]	[mm]	[pcs.]	[m <sup>2</sup> ]	[m <sup>3</sup> ]
2000	1200	30	40	96,00	2,880
		40	30	72,00	2,880
		50	24	57,60	2,880
		100	12	28,80	2,880
		150	8	19,20	2,880
		-	-	-	-
		-	-	-	-
		-	-	-	-
		-	-	-	-
		-	-	-	-
		-	-	-	-
		-	-	-	-
		-	-	-	-