

TECHNICAL DATA SHEET



PETRAVENT

Slabs of stone wool for external and internal building objects for thermal, acoustic and fire insulation

OFFICIAL DOCUMENTATION:

Declaration of Performances No. PTRL-DoP/MW/15/11





FACTORY:

PETRALANA S.A. Konstytucji 74 Street 41-905 Bytom Poland +48 32 770 05 00 office@petralana.eu

APPLICATION:

external facades insulated by light-dry method (eg sheet, cladding board, siding, lining cement and composite)

external walls with elevation of stone or glass

skeletal external and internal walls (on a wooden and metal structure)

partition walls

curtain walls

cavity walls

Release: 24.03.2017



PRODUCT CODE

PETRAVENT MW-EN13162-T5-DS(70,90)-CS(10)0,5-WS-WL(P)-MU1

DECLARED THERMAL CONDUCTIVITY COEFFICIENT λ_D

≤ 0,035 [W/mK]

DECLARED PARAMETERS									
DECLARED PROPERTIES OF THE PRODUCT ACC, TO EN 13162:2012+A1:2015	SYMBOL	CLASS OR 1	FOLERANCE	UNITS					
Class for thickness tolerances	Т	T5	-1 mm / +3 mm	[mm]					
Class for thickness tolerances	'	15	-1 % / +3 mm	[%/mm]					
Dimensional stability under 70 C and 90% humidity	DS(70,90)	≤ :	1,0	[%]					
Compressive stress at 10% deformation	CS(10/Y)	CS(1	0)0,5	[kPa]					
Tensile strength perpendicular to faces	TR	Ni	PD	[kPa]					
Point load at 5mm deformation	PL(5)	Ni	PD	[N]					
Short time water absorption	ws	≤.	1,0	[kg/m²]					
Long time water absorption	WL(P)	≤:	3,0	[kg/m²]					
Water vapour transmission	ми	М	U1	[-]					
Air flow resistivity	AFr	Ni	PD 0	[kPa s/m²]					
Reaction to fire	RtF	Α	A1 Eurocla						

DECLARED THERMAL RESISTANCE R _D																	
d [mm]	50	80	100	120	150	200	-	-	-	-	-	-	-	-	-	-	-
R _D [m ² K / W]	1,40	2,25	2,85	3,40	4,25	5,70	-	-	-	-	-	-	-	-	-	-	-

	DIMENSIONS AND PACKING											
FOI	RMAT OF PLA	TES		PACKAGES		PALLETS						
Length	Width	Thickness	No. of plates in a package	Cover surface of a package	Vo l ume of a package	No. of plates on a pallet	Cover surface of plates on a pallet	Volume of plates on a pallet				
[mm]	[mm]	[mm]	[pcs.]	[m²]	[m³]	[pcs.]	[m²]	[m³]				
		50	8	4,80	0,240	12	57,60	2,880				
	600	80	5	3,00	0,240	12	36,00	2,880				
		100	4	2,40	0,240	12	28,80	2,880				
		120	5	3,00	0,360	8	24,00	2,880				
		150	4	2,40	0,360	8	19,20	2,880				
		200	2	1,20	0,240	12	14,40	2,880				
4000		-	-	-	-	-	-	-				
1000		-	-	-	-	-	-	-				
		-	-	-	-	-	-	-				
		-	-	-	-	-	-	-				
		-	-	-	-	-	-	-				
		-	-	-	-	-	-	-				
		-	-	-	-	-	-	-				
		-	-	-		-	-	-				